

# VANOX<sup>®</sup> CDPA Solid

Antioxidant

*A high amine activity antioxidant that maximizes heat resistance in severe applications*



**Vanderbilt Chemicals, LLC**

A Wholly Owned Subsidiary of R.T. Vanderbilt Holding Company, Inc.

# VANOX<sup>®</sup> CDPA Solid

## Antioxidant

### TABLE OF CONTENTS

	PAGE
<b>VANOX<sup>®</sup> CDPA Solid</b> Antioxidant 4, 4'-Bis (alpha, alpha-dimethylbenzyl) diphenylamine	1
<b>VANOX CDPA Solid</b> vs. Naugard <sup>®</sup> 445 in HNBR	2
<b>VANOX CDPA Solid</b> Antioxidant in a Vamac <sup>®</sup> G compound	4
<b>VANOX CDPA Solid</b> Antioxidant in an Vistalon <sup>™</sup> EPDM Compound Study	6
<b>VANOX ZMTI</b> , Synergistic Antioxidant – To maximize your product's resistance to high temperature	8
<b>VANOX<sup>®</sup> CDPA Solid</b> Antioxidant Specifications	9

For sample requests, sales specifications, and Safety Data Sheets, please visit our website at [www.vanderbiltchemicals.com](http://www.vanderbiltchemicals.com)

#### VANDERBILT CHEMICALS, LLC

30 Winfield Street, P.O. Box 5150  
Norwalk, CT 06856-5150  
(203) 853-1400  
F: (203) 838-6368  
E-mail: [rubber@vanderbiltchemicals.com](mailto:rubber@vanderbiltchemicals.com)

"Certified Property" indicated a property certified on the product's Certificate of Analysis.

#### TRADEMARKS

**AGERITE, DIAK, VANAX, VANFRE, VANOX** and **VAROX** are registered trademarks of Vanderbilt Chemicals, LLC.

Responsible Care is a registered trademark of the American Chemistry Council.

Armeen is a registered trademark of Akzo Nobel Chemicals B.V.

Naugard is a registered trademark of Addivant USA, LLC.

STALITE and SUPERFLEX are registered trademarks of Emerald Polymers Materials, LLC.

Vamac ethylene acrylic elastomers is a registered trademark of E.I. du Pont de Nemours and Company or its affiliates.

Vistalon is a trademark of ExxonMobil Corporation.

UL is a registered trademark of Underwriters Laboratories Inc.

Zetpol is a registered trademark of Zeon Chemicals, L.P.

# VANOX® CDPA Solid Antioxidant

## 4,4'-Bis(alpha,alpha-dimethylbenzyl)diphenylamine


**VANOX CDPA Solid** is a low volatility, high amine activity antioxidant that is especially effective in HNBR and ACM rubbers for high temperature applications. In combination with the synergist antioxidant **VANOX ZMTI**, it provides maximum heat resistance to EPR, EPDM, IR, NBR, NR and SBR rubber compounds.

The following technical data demonstrate the equivalence of **VANOX CDPA Solid** and Naugard® 445.

### CAS Number and Chemical Structure Analysis:

**VANOX CDPA Solid** and Naugard 445:

- CAS# 10081-67-1 (99%)
- Chemical Nomenclature: 4,4'-Bis(alpha,alpha-dimethylbenzyl)diphenylamine
- Melting Point: >98°C (>208.4°F)
- Chemical Structure:



As shown in Figure 1, the FTIR comparison indicates the equivalence of the essential major components. In Figure 2, the melting points of **VANOX CDPA Solid** and Naugard 445 are identical.




Figure 1: FTIR Comparison




Figure 2: DSC Melting Point

## VANOX® CDPA Solid Antioxidant vs. Naugard® 445 in HNBR

In order to further demonstrate the equivalent performance of **VANOX CDPA Solid** and Naugard 445, and to evaluate the effect of experimental error, Rubber Laboratory testing was run in duplicate.

Compounds	A1	A2	A3	A4
Zetpol® 2020 HNBR	100.0	100.0	100.0	100.0
Zinc Oxide	5.0	5.0	5.0	5.0
Stearic Acid	0.5	0.5	0.5	0.5
N330 Carbon Black	20.0	20.0	20.0	20.0
N990 Carbon Black	45.0	45.0	45.0	45.0
<b>Naugard® 445</b>	<b>1.5</b>	<b>1.5</b>	—	—
<b>VANOX® CDPA Solid</b> Antioxidant	—	—	<b>1.5</b>	<b>1.5</b>
<b>Dicumyl 40% on Kaolin</b> Peroxide Accelerator	8.0	8.0	8.0	8.0
Totals	180.0	180.0	180.0	180.0
<b>ASTM D1646, Mooney Viscosity @ 100°C (212°F), ML1+4</b>				
Viscosity, mu	87.2	84.7	85.1	86.2
<b>Mooney Scorch at 121°C (250°F)</b>				
Minimum Viscosity, mu	55.0	53.4	53.0	53.9
t <sub>5</sub> , (min)	24.36	24.82	25.42	24.82
<b>ASTM D5289, Moving Die Rheometer @ 171°C (340°F), 0.5° Arc</b>				
Minimum Torque, M <sub>L</sub> , dN·m	1.33	1.31	1.37	1.34
Maximum Torque, M <sub>H</sub> , dN·m	25.08	25.32	25.51	25.22
t <sub>s1</sub> , (min)	0.52	0.52	0.52	0.51
t'90, (min)	6.34	6.42	6.35	6.28
Cure Rate Index, (min <sup>-1</sup> )	17.20	16.90	17.20	17.30
Cure Rate, dN.m/(min)	4.08	4.07	4.14	4.14
Tan Delta at M <sub>L</sub>	1.22	1.23	1.21	1.22
Tan Delta at M <sub>H</sub>	0.06	0.06	0.06	0.06

	A1	A2	A3	A4
	Naugard® 445	Naugard 445	VANOX® CDPA Solid Antioxidant	VANOX CDPA Solid
<b>ASTM D412, Method A, Die D, Stress Strain Tests @ 21°C (70°F)</b> (Cure test slabs t'90 + 2 minutes at 171° C)				
200% Modulus, MPa	14.84	16.11	15.93	16.22
Tensile, MPa	24.68	25.17	25.33	24.82
Elongation at Break, %	341	332	326	334
<b>ASTM D2240, Shore A Durometer @ 21°C (70°F)</b>				
Hardness, Points	66.8	67.1	67.1	66.9
<b>ASTM D573, Rubber Deterioration, 70 hrs. @ 175°C (347°F)</b>				
Retained Tensile, %	59.5	67.0	54.9	67.4
Aged Tensile, MPa	14.69	16.86	13.90	16.73
Retained Elongation, %	24.3	26.2	22.7	26.0
Aged Elongation, %	83	87	74	87
Hardness, Pts. Change	+11.4	+12.0	+12.1	+11.6
Hardness, Aged Points	78.2	79.1	79.2	78.5
<b>ASTM D573, Rubber Deterioration, 168 hrs. @ 150°C (302°F)</b>				
Retained Tensile, %	100.3	101.1	99.1	100.8
Aged Tensile, MPa	24.74	25.43	25.10	25.01
Retained Elongation, %	53.4	54.8	54.9	52.7
Aged Elongation, %	182	182	179	176
Hardness, Pts. Change	+10.0	+9.8	+9.7	+10.5
Hardness, Aged Points	76.8	76.9	76.8	77.4
<b>ASTM D395, Method B – Compression Set, 70 Hours at 150°C (302°F)</b> (Cure Buttons at t'90 + 12.5 minutes at 171° C)				
Set, %	28.7	29.7	29.8	30.3

# VANOX<sup>®</sup> CDPA Solid Antioxidant in a Vamac<sup>®</sup> G compound

VANOX CDPA Solid is a high molecular weight diphenylamine antioxidant that has successfully replaced Naugard<sup>®</sup> 445 in natural rubber and most synthetic polymers and compounds. This cost-effective antioxidant was compared to Naugard 445 in a Vamac<sup>®</sup> G compound.

Vamac<sup>®</sup> (AEM) ethylene acrylic elastomers are used in applications where flexibility is needed in combination with both heat and oil resistance. Generally 2 phr of diphenylamine are recommended in black formulations. The results of the two compounds are compared below to demonstrate the equivalent performance of VANOX CDPA Solid and Naugard 445.




Figure 3: Retained Tensile Strength and Elongation





Figure 4: Compression Set Resistance

<b>Ingredients</b>	<b>Compounds (phr)</b>	
	<b>1</b>	<b>2</b>
Vamac® G ethylene/acrylic elastomer	100.0	100.0
N774 Carbon Black	65.0	65.0
Stearic Acid	1.5	1.5
<b>VANFRE® VAM</b> Processing Aid	1.0	1.0
Armeen® 18D	0.5	0.5
<b>VANOX® CDPA Solid</b> Antioxidant	2.0	—
Naugard® 445	—	2.0
<b>VANAX® DOTG PWDR</b> Accelerator	4.0	4.0
<b>DIAK® No. 1</b> Curing Agent	1.5	1.5
Totals	175.5	175.5
<b>PHYSICAL PROPERTIES</b>		
<i>Press Cured 10 min. @ 177°C (350 °F) and Postcured 4 hrs. @ 175°C (347 °F)</i>		
100% Modulus, MPa	7.1	7.4
Tensile Strength, MPa	16.1	16.4
Elongation, %	280	259
Hardness, Shore A	70.4	70.9
<b>OVEN AGED 336 HOURS @ 175°C (347°F)</b>		
Tensile Retained, %	96.1	89.0
Elongation Retained, %	62.9	62.5
Hardness, Shore A	+5.0	+5.2
<b>COMPRESSION SET – METHOD B – PLIED – 168 HOURS @ 150°C (302°F)</b>		
Set, %	23.1	23.2
<b>COMPRESSION SET – METHOD B – PLIED – 336 HOURS @ 165°C (329°F)</b>		
Set, %	33.6	35.5
<b>MDR, ASTM D 5289 @ 177°C (350°F), 0.5°Arc</b>		
Minimum Torque, M <sub>L</sub> , dN·m	0.33	0.28
Maximum Torque, M <sub>H</sub> , dN·m	14.48	14.63
t <sub>s1</sub> , (min)	0.81	0.82
t'90, (min)	6.89	6.81

## VANOX® CDPA Solid Antioxidant in an Vistalon™ EPDM Compound Study

The selection of the correct antioxidant system that optimizes the physical properties of the finished product is extremely important in rubber compounding. This study compares the effectiveness of several antioxidants in peroxide cured EPDM. **VANOX ZMTI** has been shown to work synergistically with other antioxidants to greatly improve the retention of physical properties. **VANOX ZMTI** and **VANOX CDPA Solid** together provide the best overall results.



**Figure 5: Retained Tensile Strength and Elongation**

Ingredients	Compounds (phr)					
	1	2	3	4	5	6
	No AO	AGERITE™ TMQ	VANOX CDPA Solid	VANOX ZMTI	VANOX ZMTI + AGERITE™ TMQ	VANOX ZMTI + CDPA Solid
<b>Vistalon™ 706</b> EPDM rubber	70.0	70.0	70.0	70.0	70.0	70.0
<b>Vistalon™ 7500</b> EPDM rubber	30.0	30.0	30.0	30.0	30.0	30.0
N550 Carbon Black	110.0	110.0	110.0	110.0	110.0	110.0
Paraffinic Oil	45.0	45.0	45.0	45.0	45.0	45.0
Di- (2-tert-butylperoxyisopropyl) benzene 40% on Koalin Peroxide Accelerator	6.0	6.0	6.0	6.0	6.0	6.0
<b>VANAX® MBM PWDR</b> Accelerator	1.0	1.0	1.0	1.0	1.0	1.0
<b>VANOX® ZMTI</b> Antioxidant	-	-	-	2.0	2.0	2.0
<b>VANOX CDPA Solid</b> Antioxidant	-	-	2.0	-	-	1.0
<b>AGERITE® TMQ</b> Antioxidant	-	2.0	-	-	1.0	-
Totals	263.0	264.0	264.0	264.0	265.0	265.0



	Compounds					
	1	2	3	4	5	6
	No AO	AGERITE® TMQ	VANOX® CDPA Solid Antioxidant	VANOX ZMTI	VANOX ZMTI + AGERITE TMQ	VANOX ZMTI + VANOX CDPA Solid
<b>PHYSICAL PROPERTIES</b>						
<i>Press Cured t'90 + 2 min. @ 177°C (350°F)</i>						
100% Modulus, MPa	3.9	4.4	3.6	4.3	4.0	3.6
Tensile Strength, MPa	14.0	14.0	12.9	13.3	13.4	12.4
Elongation, %	287	304	306	272	302	283
Hardness, Shore A	67.8	69.4	65.0	70.3	68.7	67.8
<b>OVEN AGED 70 HOURS @ 175°C (347°F)</b>						
Tensile Retained, %	53.0	67.8	62.6	78.4	88.3	81.9
Elongation Retained, %	84.7	72.0	93.5	108.8	85.4	101.1
<b>OVEN AGED 168 HOURS @ 150°C (302°F)</b>						
Tensile Retained, %	73.4	83.0	77.9	96.6	96.2	92.6
Elongation Retained, %	91.3	79.6	96.4	110.7	98.3	107.4
<b>COMPRESSION SET – METHOD B – 70 HOURS @ 150°C (302°F)</b>						
Set, %	30.4	26.1	32.3	27.2	31.2	32.1
<b>MDR, ASTM D 5289 @ 177°C (350°F), 0.5°Arc</b>						
Minimum Torque, M <sub>L</sub> , dN·m	2.10	2.18	2.03	2.42	2.29	2.34
Maximum Torque, M <sub>H</sub> , dN·m	16.95	16.82	14.89	17.63	17.18	16.72
t <sub>s1</sub> , (min)	0.39	0.54	0.46	0.40	0.48	0.45
t'90, (min)	4.01	4.82	5.04	4.03	4.44	4.53

## **VANOX® ZMTI Antioxidant**

**Synergistic Antioxidant – To maximize a product's resistance to high temperature.**

Rubber compounds are often protected by the use of just one antioxidant, but more severe service conditions require the use of combinations of antioxidants.

**VANOX ZMTI** is an antioxidant that is manufactured at **Vanderbilt Chemicals, LLC** in Murray, KY. It works particularly well in combination with other antioxidants. Its synergistic effect can be demonstrated in various rubber formulations based on polymers such as EPDM, Natural Rubber, Neoprene, NBR and SBR.

**VANOX ZMTI** provides excellent protection against heat and oxygen aging, especially when combined with amine or phenolic-type antioxidants, and is also beneficial where improved flex fatigue resistance is required. The synergistic effect of **VANOX ZMTI** with other antioxidants can be demonstrated in both mineral- and carbon black-filled compounds, as well as with conventional sulfur, low sulfur, sulfur-donors, or peroxide cure systems.

**VAROX®** Peroxide Accelerator cures provide vulcanizates with maximum thermal and oxidative stability, as well as superior resistance to compression set. Most antioxidants reduce peroxide efficiency, resulting in the loss of physical properties. **VANOX ZMTI** is fully compatible with peroxide cures and gives the best results in combination with amine antioxidants such as **AGERITE® SUPERFLEX® SOLID G** Antioxidant. This synergistic combination of antioxidants also offers the best thermal stability and maximum flex fatigue resistance in conventional sulfur cure systems.

**AGERITE STALITE® S** Antioxidant is the preferred antioxidant for Neoprene. When used with **VANOX ZMTI** in either a **VAROX** peroxide or an Ethylene Thiourea (ETU) cure system, the synergistic effect is evident in the increased state of cure and improved heat resistance.

This combination also improves flex-fatigue resistance despite providing higher modulus and hardness, along with improved compression set.

In summary, **VANOX ZMTI** exhibits the following features:

- **Synergy with amines and phenol antioxidants**
- **Maximum high-temperature resistance**
- **Flex-fatigue resistance**
- **No interference with peroxide cures**
- **Nonvolatile**
- **Good color**

## VANOX® CDPA Solid Antioxidant Specifications

RTV Product Code: **54036**

Composition: **4,4'-Bis( $\alpha,\alpha$ -dimethylbenzyl)diphenylamine**

Physical State: **White powder**

	Specification	Test Method
*Ash Content	0.1% maximum	T-4
*Heat Loss 1 hr.at 70°C	0.3% maximum	T-1
*Melting Point, final	98 - 102°C	AO-001

\*Certified Property

### GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Density at 25°C	1.14 Mg/m <sup>3</sup>
-----------------	------------------------

**Uses** - Antioxidant for NR and SR.

## VANOX ZMTI Specifications

RTV Product Code: **53499**

Composition: **Zinc 2-mercaptotolumidazole**

Physical State: **Cream to light yellow powder**

	Specification	Test Method
*Fineness, through 200 mesh	99.9% minimum	T-14D
*Heat Loss 2 hrs. @ 60-65°C	2.0% maximum	T-1A
*Zinc Content	17.2-19.3%	T-365, AA-103

\*Certified Property

### GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Anti-Dusting Agent Content	3-5%
Density at 25°C	1.54 Mg/m <sup>3</sup>
Melting Point, Initial	300°C minimum
Solubility - Soluble in ethanol and methanol.	Practically insoluble in other organic solvents and water.

**Uses** - A nondiscoloring, nonstaining antioxidant for NR and SR. Particularly effective in EPDM and Nitrile stock. Suggested as a synergist with **AGERITE® STALITE® S** Antioxidant, **AGERITE™ TMQ**, and **AGERITE SUPERFLEX® SOLID G** for aging at normal or elevated temperatures. Offers excellent flex resistance in NR, SBR, NBR, and CR when combined with **AGERITE SUPERFLEX SOLID G** and **AGERITE STALITE**.



# Vanderbilt Chemicals, LLC

A Wholly Owned Subsidiary of R.T. Vanderbilt Holding Company, Inc.

## Vanderbilt Chemicals, LLC

30 Winfield Street, P.O. Box 5150

Norwalk, CT 06856-5150

(203) 853-1400 Fax: (203) 838-6368

E-Mail: [rubber@vanderbiltchemicals.com](mailto:rubber@vanderbiltchemicals.com)

[vanderbiltchemicals.com](http://vanderbiltchemicals.com)

## Vanderbilt Chemicals, LLC

6281 Beach Boulevard, Suite 204

Buena Park, California 90621

(714) 670-8084 Fax: (714) 739-1488

E-Mail: [westcoastoffice@vanderbiltchemicals.com](mailto:westcoastoffice@vanderbiltchemicals.com)

[vanderbiltchemicals.com](http://vanderbiltchemicals.com)



VANDERBILT CHEMICALS, LLC  
CERTIFIED TO ISO 9001:2015  
10002461



**RESPONSIBLE CARE**<sup>®</sup>  
OUR COMMITMENT TO SUSTAINABILITY

### TRADEMARKS

Registered and pending trademarks appearing in these materials are those of Vanderbilt Chemicals, LLC.

For a complete trademark listing, please visit the About section at [www.vanderbiltchemicals.com](http://www.vanderbiltchemicals.com).

### DISCLAIMER

Before using, read, understand and comply with the information and precautions in the Safety Data Sheets, label and other product literature. The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all-inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. Vanderbilt Chemicals, LLC does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent, trademark or copyright or to violate any federal, state or local law or regulation.

rev6/21/2019